

TECHNICAL DATA SHEET

Specifications

Code	650307
Description	Glass 300
Recommendation for application (EN 779:2012)	G4

Technical data

Composition	Glass fiber	
Net filtration area	0,372	m ²
Area weight (± 5%)	350	g/m ²
Thickness (-0/+5)	50	mm
Temperature resistance	300	°C
Initial pressure drop	58	Pa
Recommended final pressure drop	210	Pa
Dust holding capacity	282	g/m ²
Intake air velocity	1,0	m/s

Functional data

Flammability (DIN 4102)	Non-combustible
-------------------------	-----------------

Properties

- Randomly arranged fine fiber glass.
- High stability - High dust holding capacity.

The above mentioned data have been determined according to the averages obtained from a series of typical results and are intended just for reference. The technical information is subject to changes, usual tolerances apply.